

Zytel® 80G25HS BK117

NYLON RESIN

DuPont Performance Polymers

PROSPECTOR®

www.ulprospector.com

Technical Data

产品说明

25% Glass Reinforced, Toughened, Heat Stabilized, Polyamide 66

总体

材料状态	• 已商用：当前有效
资料 ¹	• Processing - Injection Molding (English) • Processing - Injection Molding of Glass-reinforced Zytel (English) • Typical Processing for DuPont Engineering Polymers (English)
搜索 UL 黄卡	• DuPont Performance Polymers • Zytel®
供货地区	• 北美洲 • 非洲和中东 • 拉丁美洲 • 欧洲 • 亚太地区
填料/增强材料	• 玻璃纤维增强材料, 25% 填料按重量
添加剂	• 热稳定剂
特性	• 热稳定性
加工方法	• 注射成型
部件标识代码 (ISO 11469)	• >PA66-IGF25<
树脂ID (ISO 1043)	• PA66-IGF25

物理性能	干燥	调节后的	单位制	测试方法
密度	1.25	--	g/cm ³	ISO 1183
收缩率 - 流动方向	0.30	--	%	ISO 294-4
粘数	140	--	cm ³ /g	ISO 307
机械性能	干燥	调节后的	单位制	测试方法
拉伸模量	1.00E+6 (6900)	682000 (4700)	psi (MPa)	ISO 527-2
拉伸应力 (断裂)	17700 (122)	12600 (87.0)	psi (MPa)	ISO 527-2
拉伸应变 (断裂)	4.0	8.0	%	ISO 527-2
弯曲模量	870000 (6000)	--	psi (MPa)	ISO 178
冲击性能	干燥	调节后的	单位制	测试方法
简支梁缺口冲击强度				ISO 179/1eA
-22°F (-30°C)	6.7 (14)	6.2 (13)	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	10 (22)	11 (24)	ft·lb/in ² (kJ/m ²)	
简支梁无缺口冲击强度				ISO 179/1eU
-22°F (-30°C)	42 (89)	41 (87)	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	39 (83)	39 (81)	ft·lb/in ² (kJ/m ²)	
悬壁梁缺口冲击强度				ISO 180/1A
-40°F (-40°C)	6.2 (13)	5.7 (12)	ft·lb/in ² (kJ/m ²)	
-22°F (-30°C)	6.2 (13)	5.7 (12)	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	9.5 (20)	11 (23)	ft·lb/in ² (kJ/m ²)	



热性能	干燥	调节后的	单位制	测试方法
热变形温度				
66 psi (0.45 MPa), 未退火	496 (258)	--	°F (°C)	ISO 75-2/B
264 psi (1.8 MPa), 未退火	464 (240)	--	°F (°C)	ISO 75-2/A
熔融温度 ³	504 (262)	--	°F (°C)	ISO 11357-3

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 10°C/min

购买地点

供应商

DuPont Performance Polymers

Wilmington, DE USA

电话: 302-999-4592

Web: <http://plastics.dupont.com/>

分销商

Biesterfeld Plastic GmbH

Biesterfeld Plastic GmbH is a Pan European distribution company. Contact Biesterfeld Plastic GmbH for availability of individual products by country.

电话: +49-40-32008-0

Web: <http://www.biesterfeld-plastic.com/>

供货地区: Algeria, Austria, Belgium, Bosnia and Herzegovina, Bulgaria, Croatia, Cyprus, Czech Republic, Egypt, France, Germany, Greece, Hungary, Italy, Libyan Arab Jamahiriya, Luxembourg, Mauritania, Morocco, Netherlands, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Switzerland, Tunisia, Turkey

PolyOne Distribution

PolyOne Distribution is a global distribution company. Contact PolyOne Distribution for availability of individual products by country.

电话: 800-894-4266

Web: <http://polyonedistribution.com/>

供货地区: Global