

Fusabond® E528

聚乙烯

DuPont Packaging & Industrial Polymers

PROSPECTOR®

www.ulprospector.com

Technical Data

产品说明

DuPont™ Fusabond® E226 is an anhydride modified polyethylene.

Uses:

- Polymer Modifier

总体

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet (English)		
搜索 UL 黄卡	• DuPont Packaging & Industrial Polymers		
供货地区	• 北美洲 • 非洲和中东	• 拉丁美洲 • 欧洲	• 亚太地区
用途	• 混合		
形式	• 粒子		

物理性能	额定值 (英制)	额定值 (公制)	测试方法
比重			
--	0.924	0.922 g/cm ³	ASTM D792
--	0.922 g/cm ³	0.922 g/cm ³	ISO 1183
熔流率 (熔体流动速率) (190°C/2.16 kg)	6.7 g/10 min	6.7 g/10 min	ASTM D1238 ISO 1133
热性能	额定值 (英制)	额定值 (公制)	测试方法
熔融温度 (DSC)	237 °F	114 °C	ISO 3146 ASTM D3418
Freezing Point - (DSC)	207 °F	97 °C	ASTM D3418
补充信息	额定值 (英制)	额定值 (公制)	
Processing Temperature	< 572 °F	< 300 °C	

备注

¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

² 一般属性：这些不能被视为规格。



Fusabond® E528

聚乙烯

DuPont Packaging & Industrial Polymers

PROSPECTOR®

www.ulprospector.com

购买地点

供应商

DuPont Packaging & Industrial Polymers

Wilmington, DE USA

电话: 800-628-6208

Web: http://www2.dupont.com/Packaging_Resins/en_US/

分销商

Nexeo Solutions

电话: 888-594-6009

Web: <http://www.nexeosolutions.com/>

供货地区: North America

PolyOne Distribution

PolyOne Distribution is a global distribution company. Contact PolyOne Distribution for availability of individual products by country.

电话: 800-894-4266

Web: <http://polyonedistribution.com/>

供货地区: Global

