

Fusabond® A560

乙烯丙烯酸酯共聚物

DuPont Packaging & Industrial Polymers

PROSPECTOR®

www.ulprospector.com

Technical Data

产品说明

DuPont™ Fusabond® A560 is a chemically modified ethylene acrylate copolymer

总体

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet (English)		
搜索 UL 黄卡	• DuPont Packaging & Industrial Polymers		
供货地区	• 北美洲 • 非洲和中东	• 拉丁美洲 • 欧洲	• 亚太地区
用途	• 塑料改性		
形式	• 粒子		

物理性能	额定值 (英制)	额定值 (公制)	测试方法
比重			
--	0.932	0.930 g/cm³	ASTM D792
--	0.930 g/cm³	0.930 g/cm³	ISO 1183
熔流率 (熔体流动速率) (190°C/2.16 kg)	5.6 g/10 min	5.6 g/10 min	ASTM D1238 ISO 1133
热性能	额定值 (英制)	额定值 (公制)	测试方法
熔融峰值温度	201 °F	94.0 °C	ASTM D3418 ISO 3146
补充信息	额定值 (英制)	额定值 (公制)	
Maximum Processing Temperature	< 500 °F	< 260 °C	

备注

¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

² 一般属性：这些不能被视为规格。



Fusabond® A560

乙烯丙烯酸酯共聚物

DuPont Packaging & Industrial Polymers

PROSPECTOR®

www.ulprospector.com

购买地点

供应商

DuPont Packaging & Industrial Polymers

Wilmington, DE USA

电话: 800-628-6208

Web: http://www2.dupont.com/Packaging_Resins/en_US/

分销商

Nexeo Solutions

电话: 888-594-6009

Web: <http://www.nexeosolutions.com/>

供货地区: North America

PolyOne Distribution

PolyOne Distribution is a global distribution company. Contact PolyOne Distribution for availability of individual products by country.

电话: 800-894-4266

Web: <http://polyonedistribution.com/>

供货地区: Global

