

Elastollan® 1195A10R

热塑性聚氨酯弹性体 (聚醚)

BASF Corp. Thermoplastic Polyurethanes

PROSPECTOR®

www.ulprospector.com

Technical Data

产品说明

Elastollan® 1195A is specifically formulated for extruded profile, sheet and film applications. It exhibits excellent abrasion resistance, toughness, transparency, very good low temperature flexibility, hydrolytic stability and fungus resistance. It has excellent damping characteristics and outstanding resistance to tear propagation. Elastollan® 1195A is rated UL-94 HB in vertical flame test for wall thicknesses of 0.75 and 3.0 mm. Elastollan® 1195A also conforms to the FDA food contact regulations as described in book 21, section 177.2600 for wet food contact applications. Elastollan® 1195A also has NSF Standard 61 "Water Contact Material" certification. Elastollan® 1195A is supplied uncolored and in diced or pelletized form.

总体

材料状态	• 已商用 : 当前有效
资料 ¹	• Processing - Elastollan (English) • Technical Datasheet (English)
搜索 UL 黄卡	• BASF Corp. Thermoplastic Polyurethanes • Elastollan®
供货地区	• 北美洲
特性	• 低温下的柔性 • 抗菌性 • 良好的撕裂强度 • 良好耐磨损性 • 韧性良好 • 食品接触的合规性 • 水解稳定
机构评级	• FDA 21 CFR 177.2600 • NSF 61
外观	• 清晰/透明
加工方法	• 挤出 • 注射成型

物理性能	额定值 (英制)	额定值 (公制)	测试方法
比重	1.14	1.14 g/cm ³	ASTM D792
熔流量 (熔体流动速率) (210°C/3.8 kg)	5.0 到 20 g/10 min	5.0 到 20 g/10 min	ASTM D1238
机械性能	额定值 (英制)	额定值 (公制)	测试方法
拉伸模量 (注塑)	7500 psi	51.7 MPa	ASTM D412
弯曲模量 (注塑)	7600 psi	52.4 MPa	ASTM D790
泰伯耐磨性	55.0 mg	55.0 mg	ASTM D1044
Abrasion - DIN	25 mm ³	25 mm ³	DIN 53516
弹性体	额定值 (英制)	额定值 (公制)	测试方法
拉伸应力			ASTM D412
100%应变	2500 psi	17.2 MPa	
300%应变	5200 psi	35.9 MPa	
抗张强度	5700 psi	39.3 MPa	ASTM D412
伸长率 (断裂)	430 %	430 %	ASTM D412
撕裂强度 ³	800 lbf/in	140 kN/m	ASTM D624
压缩永久变形			ASTM D395B
73°F (23°C), 22 hr	30 %	30 %	
158°F (70°C), 22 hr	45 %	45 %	
硬度	额定值 (英制)	额定值 (公制)	测试方法
肖氏硬度 (邵氏 A)	95	95	ASTM D2240
热性能	额定值 (英制)	额定值 (公制)	测试方法
玻璃转化温度	-18.4 °F	-28.0 °C	内部方法
维卡软化温度	261 °F	127 °C	ASTM D1525
Softening Point - DMA	192 °F	89 °C	内部方法
可燃性	额定值 (英制)	额定值 (公制)	测试方法
UL 阻燃等级			UL 94
0.0295 in (0.750 mm)	HB	HB	
0.118 in (3.00 mm)	HB	HB	



注射	额定值 (英制)	额定值 (公制)
干燥温度	230 到 248 °F	110 到 120 °C
干燥时间	2.0 到 3.0 hr	2.0 到 3.0 hr
建议的最大水分含量	0.030 %	0.030 %
料筒后部温度	374 到 428 °F	190 到 220 °C
料筒中部温度	374 到 428 °F	190 到 220 °C
料筒前部温度	374 到 428 °F	190 到 220 °C
射嘴温度	410 到 437 °F	210 到 225 °C
挤出	额定值 (英制)	额定值 (公制)
干燥温度	230 到 248 °F	110 到 120 °C
干燥时间	2.0 到 3.0 hr	2.0 到 3.0 hr
料筒1区温度	338 到 410 °F	170 到 210 °C
料筒3区温度	338 到 410 °F	170 到 210 °C
料筒5区温度	338 到 410 °F	170 到 210 °C
接头温度	392 到 428 °F	200 到 220 °C
口模温度	383 到 419 °F	195 到 215 °C

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ C 模具



Elastollan® 1195A10R

热塑性聚氨酯弹性体 (聚醚)

BASF Corp. Thermoplastic Polyurethanes

PROSPECTOR®

www.ulprospector.com

购买地点

供应商

BASF Corp. Thermoplastic Polyurethanes

Wyandotte, MI USA

电话: 800-892-3111

Web: <http://www.elastollan.com/>

分销商

Channel Prime Alliance

电话: 800-247-8038

Web: <http://www.channelpa.com/>

供货地区: North America

